



Standard Test Method for Early Stiffening of Hydraulic Cement (Paste Method)¹

This standard is issued under the fixed designation C 451; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of early stiffening in hydraulic-cement paste.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

Warning—Fresh hydraulic-cementitious mixtures are caustic and may cause chemical burns to skin and tissue upon prolonged exposure. The use of gloves, protective clothing, and eye protection is recommended. Wash contact area with copious amounts of water after contact. Wash eyes for a minimum of 15 min. Avoid exposure of the body to clothing saturated with the liquid phase of the unhardened material. Remove contaminated clothing immediately after exposure.

2. Referenced Documents

2.1 ASTM Standards:²

- C 150 Specification for Portland Cement
- C 183 Practice for Sampling and the Amount of Testing of Hydraulic Cement
- C 187 Test Method for Normal Consistency of Hydraulic Cement
- C 219 Terminology Relating to Hydraulic Cement
- C 305 Practice for Mechanical Mixing of Hydraulic Cement Pastes and Mortars of Plastic Consistency
- C 670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials
- C 1005 Specification for Reference Masses and Devices for Determining Mass and Volume for Use in the Physical Testing of Hydraulic Cements

¹ This test method is under the jurisdiction of ASTM Committee C01 on Cement and is the direct responsibility of Subcommittee C01.30 on Time of Set.

Current edition approved Jan. 1, 2004. Published February 2004. Originally approved in 1960. Last previous edition approved in 1999 as C 451 – 99.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D 1193 Specification for Reagent Water

3. Terminology

3.1 Definitions:

3.1.1 *early stiffening, n*—the early development of stiffness in the working characteristics of a hydraulic-cement paste, mortar, or concrete; varieties include false set and flash set.

3.1.2 *false set, n*—the early development of stiffness in the working characteristics of a hydraulic-cement paste, mortar, or concrete without the evolution of much heat, which stiffness can be dispelled and plasticity regained by further mixing without addition of water; also known as “grab set,” “premature stiffening,” “hesitation set,” and “rubber set.”

3.1.3 *flash set, n*—the early development of stiffness in the working characteristics of a hydraulic-cement paste, mortar, or concrete, usually with the evolution of considerable heat, which stiffness cannot be dispelled nor can the plasticity be regained by further mixing without addition of water; also known as “quick set.”

3.1.4 Refer to Terminology C 219 for definitions of other terms.

4. Summary of Test Method

4.1 A paste is prepared with the cement to be tested, using sufficient water to give a required initial penetration as measured by the Vicat apparatus at a stipulated time after completion of mixing. A second penetration, termed the final penetration, is measured at a later stipulated time. The ratio of final penetration to initial penetration is calculated as a percentage.

5. Significance and Use

5.1 The purpose of this test method is to determine the degree to which a cement paste develops early stiffening or to establish whether or not a cement complies with a specification limit on early stiffening.

5.2 When used for establishing compliance with a specification limit, the specification requirement is customarily stated in terms of the minimum allowable final penetration, in percent, calculated in accordance with the Calculation Section. When used for estimating the relative tendency of a cement to manifest early stiffening, additional information of value may be obtained if the remix procedure described in the Procedure Section is employed. Under some conditions, a judgment may



be made by comparing the behavior in the initial test and in the remix procedure to differentiate a relatively less serious and less persistent tendency to early stiffening (false set) from one that is more persistent and, consequently, more serious (flash set).

5.3 Severe false setting in a cement may cause difficulty from a placing and handling standpoint, but it is not likely to cause difficulties where concrete is mixed for a longer time than usual, as usually occurs in transit mixing, or where it is remixed prior to placing or transporting, as occurs in concrete pumping operations. It is most likely to be noticeable where concrete is mixed for a short period of time in stationary mixers and transported to the forms in non-agitating equipment, such as on some paving jobs, and when concrete is made in an on-site batch plant.

5.4 Cements with severe false setting usually require slightly more water to produce the same consistency, which may be expected to result in slightly lower strengths and increased drying shrinkage.

5.5 Early stiffening caused by flash set usually will cause the cement to fail the appropriate time of setting specification requirements for the cement.

5.6 Early stiffening caused by false set is not likely to cause a cement to fail the appropriate time of setting requirement.

6. Apparatus

6.1 *Vicat Apparatus*, conforming to the requirements of Test Method C 187.

6.2 *Trowel*, having a steel blade 100 to 150 mm (4 to 6 in.) in length, with straightedge.

6.3 *Mixer, Bowl, Paddle, and Scraper*, conforming to the requirements of Practice C 305.

6.4 *Glass Graduates*, conforming to the requirements of Specification C 1005.

6.5 *Masses and Mass Determining Devices* conforming to the requirements of Specification C 1005.

7. Reagent

7.1 *Mixing Water*—Potable water is satisfactory for routine tests. For all referee and cooperative tests, use reagent water conforming to the requirements of Specification D 1193 for Type III or Type IV grades of reagent water.

8. Sampling

8.1 When the test is part of acceptance testing, sample the cement in accordance with Practice C 183.

9. Conditioning

9.1 Maintain the temperature of the room, dry materials, paddle, bowl, conical ring, and base plate at $23.0 \pm 3.0^\circ\text{C}$. Maintain the temperature of the mixing water at $23.0 \pm 2.0^\circ\text{C}$.

9.2 Maintain the relative humidity of the laboratory at not less than 50 %.

10. Procedure

10.1 *Preparation of Cement Paste*—Mix 500 g of cement with sufficient water to produce a paste with an initial penetration of 32 ± 4 mm using the following procedure.

10.1.1 Place the dry paddle and the dry bowl in the mixing position in the mixer.

10.1.2 Introduce the materials for a batch into the bowl and mix in the following manner:

10.1.2.1 Place all the mixing water in the bowl.

10.1.2.2 Add the cement to the water and allow 30 s for the water to absorb.

10.1.2.3 Start the mixer and mix at a slow speed (140 ± 5 r/min) for 30 s.

10.1.2.4 Stop the mixer for 15 s, and during this time scrape down into the batch any paste that may have collected on the sides of the bowl.

10.1.2.5 Start the mixer at a medium speed (285 ± 10 r/min) and mix for $2\frac{1}{2}$ min.

10.2 *Molding Test Specimens*—Quickly form the cement paste into a ball with gloved hands. Press the ball, resting in the palm of one hand, into the larger end of the conical ring G, Fig. 1 of Test Method C 187, held in the other hand, completely filling the ring with paste. Remove the excess at the larger end by a single movement of the palm of the hand. Place the ring on its larger end on a plate, H, and slice off the excess paste at the smaller end at the top of the ring by a single oblique stroke of a sharp-edged trowel held at a slight angle with the top of the ring. Smooth the top of the specimen, if necessary, with one or two light touches of the pointed end of the trowel. During the operation of cutting and smoothing, take care not to compress the paste.

10.3 *Determination of Initial Penetration*—Set the paste confined in the ring resting on the plate, H, under the rod, B, Fig. 1 of Test Method C 187, about one third of the diameter from the edge, and the plunger end, C, shall be brought in contact with the surface of the paste and the tightened setscrew, E. Then set the movable indicator, F, to the upper zero mark of the scale, and release the rod exactly 20 s after completion of the mixing. Keep the apparatus free of all vibrations during the penetration test. Consider the paste to have proper consistency when the rod settles to a point 32 ± 4 mm below the original surface in 30 s after being released. Make trial pastes with varying percentages of water until this consistency is obtained. This consistency is the initial penetration. During the 30-s interval for the initial penetration, return the excess paste to the bowl and cover the bowl and mixing paddle with a lid.

10.4 *Determination of Final Penetration*—After completion of the initial reading, remove the plunger from the paste, clean it, and reset the ring and plate in a new position. Perform this operation with as little disturbance as possible to the paste confined in the Vicat ring. Then bring the plunger again in contact with the surface of the paste, tighten the setscrew, and set the movable indicator to the upper zero mark of the scale. Release the plunger a second time 5 min after completion of the mixing period, and determine the final penetration 30 s after the plunger is released.

10.5 *Determination of Remix Penetration*—If the penetrations determined by the foregoing procedure show the cement to be stiffening rapidly, at the option of the tester, obtain information as to the nature of the stiffening by testing as follows:

10.5.1 After completing the measurement of the 5-min penetration, immediately return the paste in the ring to the bowl.

10.5.2 Start the mixer, raise the bowl into mixing position, and remix the contents of the bowl at a medium speed (285 ± 10 r/min) for 1 min.

10.5.3 Fill the ring and determine the penetration following the procedures specified in 10.2 and 10.3.

11. Calculation

11.1 Calculate the percent final penetration, based on the ratio of final penetration to initial penetration, as follows:

$$P, \% = \frac{B}{A} \times 100 \quad (1)$$

where:

- P = percent final penetration,
- A = initial penetration, mm, and
- B = final penetration, mm.

12. Report

12.1 Report the results of the test as follows:

Initial penetration	___ mm
Final penetration	___ mm
Percent final penetration	___ %
Remix penetration	___ mm

13. Precision and Bias

13.1 Precision

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

13.1.1 On samples testing between 8 % and 89 % Paste False Set, the single-operator (within laboratory) standard deviation has been found to be 10 % (1s), therefore, results of two properly conducted tests by the same operator on samples of the same cement should not differ from each other by more than 28 % (1s and d2s are defined in Practice C 670).

13.1.2 On samples testing between 8 % and 89 % Paste False Set, the multi-laboratory standard deviation has been found to be 12 % (1s), therefore, results of two properly conducted tests from two different laboratories on samples of the same cement should not differ by more than 34 % (1s and d2s are defined in Practice C 670). (See Note 1.)

13.2 Bias

13.2.1 Since an acceptable reference material suitable for determining any bias of this method does not exist, no statement on bias is being made.

NOTE 1—This data is based upon CCRL Portland Cement round robin test samples 47 to 138. The data indicates that precision decreases as the false set values fall below approximately 60 %. These decreases are not clearly statistically significant, however they do indicate the duplication difficulties on cements which exhibit false set tendencies severe enough to fail or possibly fail specification C 150 optional limits.

14. Keywords

14.1 early stiffening; false set; flash set; hydraulic-cement paste; Vicat.

